



# New Guard Coatings Group

□ A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

• USA •



[www.newguardcoatings.com](http://www.newguardcoatings.com)

 [usasales@newguardcoatings.com](mailto:usasales@newguardcoatings.com)

 +1 (302) 257 5760

## Barrier 90

### Product description

This is a two component polyamide cured zinc rich epoxy coating. It is a very high zinc dust containing product. It conforms to the compositional requirements of SSPC paint 20, level 1, ISO 12944-5, BS 4652, BS 5493, and AS/NZS 3750.9.1994. It provides excellent corrosion protection as part of a complete coating system. To be used as primer in atmospheric environments. Suitable for carbon steel, repair of inorganic zinc silicate coating and damaged galvanized steel substrates. This product complies with ASTM D520 type II zinc dust.

### Typical use

Protective:

Suitable for structural steel and piping exposed in corrosivity categories up to C5 (ISO 12944-2). Recommended for offshore environments, refineries, power plants, bridges, buildings, mining equipment and general structural steel. Specially designed as a primer for coating systems where extended durability is required. Approved in a range of bridge specifications requiring 90% zinc dust content.

### Colors

grey

### Product data

| Property              | Test/Standard     | Description   |
|-----------------------|-------------------|---------------|
| Solids by volume      | ISO 3233          | 58 ± 2 %      |
| Gloss level (GU 60 °) | ISO 2813          | matt (0-35)   |
| Flash point           | ISO 3679 Method 1 | 81 °F (27 °C) |
| Density               | calculated        | 2.9 kg/l      |

  

| Region | Regulation                       | Test Standard    | VOC Value    |
|--------|----------------------------------|------------------|--------------|
| US     | CARB(SCM)2020 / SCAQMD rule 1113 | US EPA Method 24 | 3.13 lbs/gal |

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

## Film thickness per coat

### Typical recommended specification range

|                            |   |  |
|----------------------------|---|--|
| Dry film thickness         | 1 mils (25 µm)                                    | 4 mils (90 µm)                                   |
| Wet film thickness         | 1.8 mils (45 µm)                                  | 6 mils (155 µm)                                  |
| Theoretical spreading rate | 950 ft <sup>2</sup> /gal (23.2 m <sup>2</sup> /l) | 260 ft <sup>2</sup> /gal (6.4 m <sup>2</sup> /l) |

## Surface preparation

### Surface preparation summary table

| Substrate         | Surface preparation   |  |
|-------------------|---|--|
|                   | Minimum   | Recommended  |
| Carbon steel      | St 3 (ISO 8501-1) or SSPC SP-3                                  | Sa 2½ (ISO 8501-1) or NACE No. 2 / SSPC SP-10  |
| Shop primed steel | Clean, dry and undamaged approved shop primer (ISO 12944-4 5.4) | Sweep blasted or alternatively blasted to Sa 2 (ISO 8501-1) or SP 6 / NACE No. 3 (SSPC-VIS 1) of at least 70 % of the surface. |

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

## Application

### Application methods

The product can be applied by

|        |   |
|--------|---|
| Spray: | Use airless spray.  |
| Brush: | Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness. |

### Product mixing ratio (by volume)

|                   |           |
|-------------------|-----------|
| Barrier 90 Comp A | 6 part(s) |
| Barrier 90 Comp B | 1 part(s) |

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

### Guiding data for airless spray

Nozzle tip (inch/1000): 15-21  
Pressure at nozzle (minimum): 150 bar/2100 psi

## Drying and Curing time

| Substrate temperature       | 41 °F  | 50 °F  | 73 °F  | 104 °F |
|-----------------------------|--------|--------|--------|--------|
| Surface (touch) dry         | 50 min | 20 min | 10 min | 4 min  |
| Walk-on-dry                 | 3 h    | 2 h    | 1.5 h  | 40 min |
| Dried to over coat, minimum | 3 h    | 2 h    | 1.5 h  | 40 min |
| Dried/cured for service     | 10 d   | 7 d    | 5 d    | 2 d    |

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

| Paint temperature | 73 °F  |
|-------------------|--------|
| Induction time    | 30 min |
| Pot life          | 24 h   |

## Heat resistance

|                  | Temperature |        |
|------------------|-------------|--------|
|                  | Continuous  | Peak   |
| Dry, atmospheric | 120 °C      | 140 °C |

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: inorganic zinc shop primer  
Subsequent coat: polyurethane, epoxy, epoxy mastic

## Packaging (typical)

|                   | <b>Volume<br/>(liters)</b> | <b>Size of containers<br/>(liters)</b> |
|-------------------|----------------------------|--|
| Barrier 90 Comp A | 7.5                        | 10                                     |
| Barrier 90 Comp B | 1.25                       | 3                                      |

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Shelf life at 73°F (23 °C)

|                   |             |
|-------------------|-------------|
| Barrier 90 Comp A | 24 month(s) |
| Barrier 90 Comp B | 24 month(s) |

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## Color variation

When applicable, products primarily meant for use as primers or antifouling may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.